



WATERPROOF
FLASHING

www.achard-sa.com
A FIRM OF THE TERREAL GROUP



FLEXALU® is a waterproof flashing, made of aluminum and polyethylene. It is used to seal the base between walls and roof tiles, solar panels and chimneys.

PRODUCT FEATURES

Materials

Aluminium: state 0 single-sided varnish

Reinforced Polyethylene:

Total thickness 0.22 mm (**Aluminum: 0.150 mm**
+ **Polyethylene: 0.07 mm**)

BK-Butyl Width: 20 mm + 100 mm x W: 1.4 mm
with adhesive film made of silicone paper

Peel strength 180 °: 16N / cm peel strength
180 ° on concrete at 5 ° C: 32N / cm

Measurements

Length: 5000 mm

Tolerances Length : + or - 1 %

Width: 242 mm, 325 mm, 492 mm

Tolérances largeur: + or - 1 mm

Stretch: 30% lengthwise

Roll weight: 5 ML: 2kg for 333mm;

2.5kg for 500mm

Cardboard box: 30 ml (10 ml rolls),
20 ml (5 ml rolls)

Pallet: 480 ml (10 ml rolls),
280 ml (5 ml rolls)

Conformity tests performed

Aging: Standard NF T30 049 (1000 hours)


Tensile Strength: ATSM Standard D-882

Tear resistance: ISO 6383-1 standard

Resistance to temperature: DIN 52133 standard

Storage: The Product remains unaltered for a long period, however it is recommended to use the product within 12 months following the date of manufacture. The product must be stored in its original unopened packaging and stored in a dry and well-ventilated storage, with temperatures between + 5 ° C and + 40 ° C. Any storage above 50 ° C temperatures may cause difficulties in removing the protective film when installing the Product.

BREVET 1055122



LG : 5ML

	LG : 333	LG : 500
■		FLEXALU500R_20/100
■	FLEXALU330G_20/100	FLEXALU500G_20/100

PRODUCTS STRENGTH

- ✓ Easily handle for various use
- ✓ High adhesion butyl rubber blend
- ✓ Perfect sealing

COLORS



Brick red



Charcoal
Grey



Nos fabrications sont assurées auprès de GENERALI lard contrat n°AL383783 au titre de la responsabilité du fabricant. Nous nous réservons le droit d'apporter toutes modifications jugées utiles à nos produits.

260 Rue Thimonnier - BP 90050
69727 Genay Cedex - FRANCE
Tél : +33 4 72 08 72 90
Fax : +33 4 78 91 32 47

